

LOOSE TILES KA EASY FIX

# WHITE CEMENT KE ADVANTAGE WALA BIRLA WHITE TILESTIX

FINISH MAST. PAKAD JABARDAST.



# TILELYNK - TILE GROUT

Birla White TileLynk is a high quality, advanced polymer-modified, high performance grout with excellent water repellent and efflorescence resistance properties. Birla White TileLynk has higher strength and more water and stain resistance compared to normal cement grout.



**DURABLE AND  
FLEXIBLE**



**FOR TILE JOINTS  
1-6 MM GAP**



**HIGHEST WATER  
RESISTANCE**



## Features and Advantages:

- Ready to use; and only onsite mixing with water is required.
- Can be used for both interior and external applications.
- Can be used for filling up to 6 mm grout width.
- Gives non shrink, water and UV resistant grouting results.

## Suitable for:

Grouting glazed tiles, mosaic, vitrified and fully vitrified tiles, ceramic tiles, industrial tiles, granites, marbles and other natural stones etc.

## Packaging: 1 kg bag

## Technical Specifications:

Pot Life	EN 13888-1-2022	*Shelf life	Colour
1hrs.	CG-2WA	12 months	White

PROPERTIES AS PER EN 13888 -1 - 2022 (CG-2WA)	Test Method	Requirement	Test Results
1. Compressive Strength – Dry, N/mm <sup>2</sup>	EN 13888	≥ 15	> 22
2. Compressive Strength – Freeze Thaw Cycle, N/mm <sup>2</sup>	EN 13888	≥ 15	> 18
3. Flexural Strength – Dry, N/mm <sup>2</sup>	EN 13888	≥ 2.5	> 6
4. Flexural Strength – Freeze Thaw Cycle, N/mm <sup>2</sup>	EN 13888	≥ 2.5	> 5
5. Water Absorption after 30 minutes, gms	EN 13888	< 2	< 1.6
6. Water Absorption after 240 minutes, gms	EN 13888	< 5	< 3.7
7. Shrinkage, mm/m	EN 13888	< 3	< 0.2
8. Abrasion Resistance, mm <sup>3</sup>	EN 12808	≥ 1000	< 800

\*For sealed pack when stored under cover, out of direct sunlight, damp-proof condition and protect from extremes of temperature.

## Physical Properties @ 25°C

Variant	TileLynk
Mixing Ratio by weight	0.34 – 0.36
Mixed Density, kg/liter	1.65 – 1.85
Pot Life, hours	1
Sag Resistance	Non-Sag
Setting Time, hours	24
Time to Foot Traffic, hours	24
Time to Heavy Traffic, hours	7 days
Width Thickness, mm	Up to 6 mm
Application Temperature (Substrate and Materials), °C	5 - 35







ADITYA BIRLA

BUILDING  
SOLUTIONS

# BIRLA WHITE TILESTIX RANGE



Use Birla White Tilelynk for excellent results.



Scan to  
Know More

### **Birla White - A Unit of UltraTech Cement Limited,**

9th Floor, Birla Centurion, Pandurang Budhkar Marg,  
Worli, Mumbai - 400030

Website: [www.birlawhite.com](http://www.birlawhite.com) | Toll Free No.: 1800 11 1717

[www.facebook.com/BirlaWhiteCement](https://www.facebook.com/BirlaWhiteCement) | [twitter.com/BirlaWhite](https://twitter.com/BirlaWhite)

[bw-consumercare@adityabirla.com](mailto:bw-consumercare@adityabirla.com)