

LOOSE TILES KA EASY FIX

WHITE CEMENT KE
ADVANTAGE WALA
BIRLA WHITE

TILESTIX

FINISH MAST. PAKAD JABARDAST.



TILESTIX INTERO

It is a polymer modified, White Cement-based thin-set tile adhesive for fixing high porosity tiles like ceramic/clay tiles and terracotta.



DURABLE



**HIGHER
ADHESION**



EASE OF USE



**BETTER
OPEN TIME**



Features and Advantages:

- Can be used in internal areas, for floor applications.
- Water resistant - suitable for wet areas.
- Self-curing properties, which allows hassle-free application with minimum labor.
- Low VOC for healthy living.

Suitable for:

Horizontal surfaces over the cementitious substrate for indoor application in dry and wet areas.

Packaging: 20 kg bag

Technical Specifications:

Pot Life	Tensile Adhesion	Shear Adhesion	**Coverage	IS 15477: 2019	*Shelf life
2hrs.	> 0.7 N/mm ²	> 1.10 N/mm ²	Approx. 55-60 ft ²	Type 1'T'	12 months

* For sealed pack when stored under cover, out of direct sunlight, damp-proof condition and protect from extremes of temperature.

** Coverage will vary depending on trowel notch size, type and size of tile and substrate smoothness and evenness. For 20 kg bag at 3 mm thickness using 6 mm x 6 mm square notched trowel.

Application Areas:

Interior Floors	Intero
Ceramic Tiles	✓
Semi Vitreous	✓
Tile On Tile	
Vitrified Tiles	
Porcelain Tiles	
Glass Mosaics	
Natural Stones - Granite/Marble	
Small Format Tiles	✓
Medium Format Tiles	
Large Format Tiles	

Properties As Per Is 15477: 2019

Variant	Intero	
Conforms to:	1T	
Testing Properties	Requirement	Test Results
1.Tensile Adhesion Strength		
a) Dry Condition, N/mm2	Minimum 0.5	>0.7
b) Wet Condition, N/mm2		
2.Shear Adhesion Strength		
a) Dry Condition, N/mm2	Minimum 1.0	>1.10
b) Wet Condition, N/mm2		
c) Heat Aging, N/mm2		
3.Slip Resistance, mm	≤ 0.5	<0.4

Physical Properties @ 25°C

Variant	Intero
Mixing Ratio by weight	0.20 - 0.24
Mixed Density, kg/liter	1.65 - 1.85
Open Time, minutes (IS 15477: 2019)	Approx. 20
Adjustability, minutes (IS 15477: 2019)	Approx. 20
Pot Life, hours	2
Sag Resistance	-
Setting Time, hours	24
Time to Foot Traffic, hours	-
Time to Heavy Traffic, hours	24
Adhesive Thickness, mm	3 - 12
Width Thickness, mm	-
Application Temperature (Substrate and Materials), °C	5 - 35





ADITYA BIRLA

BUILDING
SOLUTIONS

BIRLA WHITE TILESTIX RANGE



Use Birla White Tilelynk for excellent results.



Scan to
Know More

Birla White - A Unit of UltraTech Cement Limited,

9th Floor, Birla Centurion, Pandurang Budhkar Marg,
Worli, Mumbai - 400030

Website: www.birlawhite.com | Toll Free No.: 1800 11 1717

www.facebook.com/BirlaWhiteCement | twitter.com/BirlaWhite

bw-consumercare@adityabirla.com